


Mild & Low Alloy Steel Flux Cored Welding Parameters

Typical Welding Parameters of Mild & Low Alloy Steel FCAW (FLUX CORED)							
Diameter of Wire		FLAT		VERTICAL-UP		OVERHEAD	
Inches	Millimeters	Voltage (V)	Amperage (A)	Voltage (V)	Amperage (A)	Voltage (V)	Amperage (A)
.035	0.9	20-30	130-250	16-23	90-180	20-28	130-240
.045	1.14	23-30	150-280	22-26	150-250	24-29	150-250
1/16	1.6	25-34	180-400	21-27	180-300	24-30	180-310

AWS CLASSIFICATION OF FLUX CORED WIRE

AWS A5.20



Page52 Data contained in this publication are typical of the products and properties described, but are not suitable for specifications.

OXFORD ALLOYS is a registered trademark of Oxford Alloys, Inc.