



TECHNIWELD 6013

TECHNIWELD 6013 is an all-purpose electrode that can be used with either AC or DC operation. Originally developed for light gage metal, it offers sufficient penetration for welding on heavier assemblies. Ideal for general purpose fabrication, machine parts, metal buildings and structures, and shaft build-up.

Features

- All position
- Slag removes easily
- Excellent arc stability
- Fast-freeze

Benefits

- Welds in flat, horizontal, vertical, and overhead positions
- Quick clean-up
- Welding accuracy and efficiency
- Excellent for poor fit-up

Typical Weld Metal Chemistry

Carbon	.10
Manganese	.28
Silicon	.27
Phosphorus	.012
Sulphur	.016

Typical Mechanical Properties

Tensile Strength	72,600 psi (501MPa)
Yield Strength	61,300 psi (423 MPa)
Elongation	26.5 %
Reduction of Area	25% to 55%

Recommended Operating Parameters

Dia.	Type of Power	Optimum Amps
3/32"	AC. DCN or DCEP	70
1/8"	AC. DCN or DCEP	100
5/32"	AC. DCN or DCEP	150
3/16"	AC. DCN or DCEP	190

For out of position welding, reduce amperages shown by 15%

Specifications

AWS A5.1 ASME SFA5.1 Class E6013

Standard Sizes

3/32" (2.4mm), 1/8" (3.2mm), 5/32" (4.0mm), 3/16" (5.0mm)

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Techniweld expressly disclaims any liability incurred from any reliance thereon. Typical data are obtained when welded and tested in accordance with AWS A5.1 specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by Techniweld.